

A

BIRCH, STEWART, KOLASCH & BIRCH, LLP

INTELLECTUAL PROPERTY LAW

8110 GATEHOUSE ROAD

SUITE 500 EAST

FALLS CHURCH, VA 22042

USA

(703) 205-8000

FAX: (703) 205-8050

(703) 698-8590 (G IV)

e-mail: mailroom@bskb.com

web: <http://www.bskb.com>

SENIOR COUNSEL:
ANTHONY L. BIRCH

JOHN W. BAILEY
JOHN A. CASTELLANO, III
GARY D. YACURA
SUSAN S. MORSE
THOMAS S. AUCHTERLONIE
EDWARD H. SIKORSKI
MICHAEL R. CAMMARATA
JAMES T. ELLER, JR.
SCOTT L. LOWE
JOSEPH H. KIM, PH.D.*
RICHARD S. MYERS, JR.*
MARY ANN CAPRIA*
MICHAEL J. CORNELISON*
MARK J. NUEL, PH.D.

REG. PATENT AGENTS:
FREDERICK R. HANDREN
ANDREW J. TELESZ, JR.
MARYANNE LIOTTA, PH.D.
MAKI HATSUMI
D. RICHARD ANDERSON
STEVEN P. WIGMORE
ESTHER H. CHIN
MIKE S. RYU
W. KARL RENNER

01/16/98
TERRELL C. BIRCH
RAYMOND C. STEWART
JOSEPH A. KOLASCH
JAMES M. SLATTERY
BERNARD L. SWEENEY*
MICHAEL K. MUTTER
CHARLES GORENSTEIN
GERALD M. MURPHY, JR.
LEONARD R. SVENSSON
VERRY L. CLARK
ANDREW D. MEIKLE
MARC S. WEINER
JOE MCKINNEY MUNCY
ANDREW F. REISH
ROBERT J. KENNEY
C. JOSEPH FARACI
DONALD J. DALEY

OF COUNSEL:
HERBERT M. BIRCH (1905-1996)
PAUL M. CRAIG, JR.*
ELLIOT A. GOLDBERG*
WILLIAM L. GATES*
EDWARD H. VALANCE
RUPERT J. BRADY*

*ADMITTED TO A BAR OTHER THAN VA

Date: January 16, 1998

Docket No.: 0020-4362P

Assistant Commissioner for Patents
Box PATENT APPLICATION
Washington, D.C. 20231

Sir:

Transmitted herewith for filing is the patent application of

Inventor(s): YAMANA, Masayuki
YAMAMOTO, Ikuo; FUKUDA, Teruyuki

For: STAINPROOFING AGENT

Enclosed are:

X A specification consisting of 38 pages

 sheet(s) of drawings

X An assignment of the invention

 Certified copy of Priority Document(s)

X Executed Declaration X Original Photocopy

 A verified statement to establish small entity status under 37
CFR 1.9 and 37 CFR 1.27

 Preliminary Amendment

 Information Disclosure Statement, PTO-1449 and reference(s)

Other _____

The filing fee has been calculated as shown below:

LARGE ENTITY				SMALL ENTITY	
FOR	NO. FILED	NO. EXTRA	RATE FEE		RATE FEE
BASIC FEE	***** ***** *****	***** ***** *****	***** ***** \$790.00 *****	or	**** **** \$395.00 ****
TOTAL CLAIMS	33 - 20 =	13	x22 =\$ 286.00	or	x 11 = \$ 0.00
INDEPENDENT	2 - 3 =	0	x82 =\$ 0.00	or	x 41 = \$ 0.00
MULTIPLE DEPENDENT CLAIM PRESENTED <u>yes</u>			+270 = \$270.00	or	+135 = \$ 0.00
TOTAL \$1,346.00				TOTAL \$ 0.00	

X A check in the amount of \$1,386.00 to cover the filing fee and recording fee (if applicable) is enclosed.

_____ Please charge Deposit Account No. 02-2448 in the amount of \$_____. A triplicate copy of this transmittal form is enclosed.

_____ No fee is enclosed.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. 1.16 or under 37 C.F.R. 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By 

RAYMOND C. STEWART

Reg. No. 21,066

P. O. Box 747

Falls Church, Virginia 22040-0747

(703) 205-8000
RCS/djm

TITLE OF THE INVENTION

STAINPROOFING AGENT

FIELD OF THE INVENTION

The present invention relates to a stainproof treatment agent. More particularly, the present invention relates to a stainproofing agent comprising a specific copolymer having a fluoroalkyl group and a specific blender copolymer. The stainproofing agent of the present invention is particularly useful for a carpet.

RELATED ART

In order to impart the water repellency, oil repellency and stainproofing properties to a textile (e.g. carpet), various stainproofing agents have hitherto been suggested. Japanese Patent Kokoku Publication Nos. 17109/1988, 55515/1991 and 55516/1991 disclose that a stainproofing agent comprising an urethane compound and a specific blender copolymer imparts the water repellency, oil repellency and stainproofing properties. However, the water repellency, oil repellency and stainproofing properties after cleaning are insufficient according to these copolymers.

Japanese Patent Kokai Publication No. 59277/1983 also discloses a water- and oil-repellent comprising a copolymer containing vinyl chloride, and the water repellency and oil repellency before and after cleaning are almost the same but the stainproofing properties are insufficient.

Japanese Patent Kokoku Publication No. 28147/1989 discloses a composition for treating a carpet, comprising an adipate ester (low molecular weight) and a blender. However, this composition can not impart sufficient water repellency, oil repellency and stainproofing properties after cleaning.

None of stainproofing agents, which have hitherto been suggested, has sufficient water- and oil-repellency as well as stainproofing properties before and after cleaning.

SUMMARY OF THE INVENTION

5 An object of the present invention is to provide a stainproofing agent having durability capable of maintaining sufficient water- and oil-repellency and stainproofing properties after cleaning.

The present invention provides a stainproofing agent comprising:

(A) a fluoroalkyl group-containing copolymer comprising

10 (I) a structure unit derived from a monomer having a fluoroalkyl group,

(II) a structure unit derived from a monomer containing no fluorine,

(III) a structure unit derived from vinyl chloride, and

(IV) a structure unit derived from a crosslinking monomer;

(B) an urethane compound having a fluoroalkyl group, or a copolymer

15 having:

(V) a structure unit derived from a monomer having a fluoroalkyl group,

and

(VI) a structure unit derived from a monomer which contains no fluorine atom and has at least one urethane or urea linkage and one carbon-carbon
20 double bond; and

(C) an acrylic copolymer containing no fluorine.

The present invention also provides a stainproofing agent comprising the above copolymer (B) and copolymer (C).

DETAILED DESCRIPTION OF THE INVENTION

25 The fluoroalkyl group is preferably a perfluoroalkyl group. The structure

unit (I) is preferably a structure unit derived from (meth)acrylate ester having a fluoroalkyl group. The monomer constituting the structure unit (I) is preferably one represented by the general formula (1):


















5 wherein Rf is a linear or branched fluoroalkyl group having 3 to 20 carbon atoms;

R¹ is a linear or branched alkylene group having 1 to 20 carbon atoms, a group of -SO₂N(R³)R⁴- or a group of -CH₂CH(OR⁵)CH₂- (R³ is an alkyl group having 1 to 10 carbon atoms; R⁴ is a linear or branched alkylene group having 1 to 10 carbon atoms; and R⁵ is a hydrogen atom or an acyl group having 1 to 10 carbon atoms); and

R² is a hydrogen atom or a methyl group.


Examples of the monomer include the followings, but are not limited thereto.





The structure unit (II) is preferably derived from a vinyl monomer containing no fluorine. Examples of the preferable monomer constituting the structure unit (II) include ethylene, vinyl acetate, vinylidene halide, acrylonitrile, styrene, alkyl (meth)acrylate, polyethylene glycol (meth)acrylate, polypropylene glycol (meth)acrylate, methoxypolyethylene glycol (meth)acrylate, methoxypolypropylene glycol (meth)acrylate, vinyl alkyl ether and isoprene, but are not limited thereto.

The monomer constituting the structure unit (II) may be (meth)acrylate ester having an alkyl group. The number of carbon atoms of the alkyl group may be from 1 to 30, e.g. from 6 to 30, specifically from 10 to 30. For example, the monomer constituting the structure unit (II) may be acrylates represented by the general formula:



wherein B^1 is a hydrogen atom or a methyl group; and B^2 is an alkylene group represented by $\text{C}_n\text{H}_{2n+1}$ ($n=1-30$). By copolymerizing these monomers, the

water- and oil-repellency and stainproofing properties as well as various characteristics (e.g. cleaning resistance, washing resistance and wear resistance of these properties, solubility in solvent, hardness and feeling) can be improved.

5 The crosslinking monomer constituting the structure unit (IV) may be a vinyl monomer which has at least two reactive groups but contains no fluorine. The crosslinking monomer may be a compound having at least two carbon-carbon double bonds, or a compound having at least one carbon-carbon double bond and at least one reactive group.

10 Examples of the crosslinking monomer include diacetone acrylamide, (meth)acrylamide, N-methylol acrylamide, hydroxymethyl (meth)acrylate, hydroxyethyl (meth)acrylate, 3-chloro-2-hydroxypropyl (meth)acrylate, N,N-dimethylaminoethyl (meth)acrylate, N,N-diethylaminoethyl (meth)acrylate, butadiene, chloroprene, glycidyl (meth)acrylate, 2-methacryloyloxyethyl
15 succinate, acrylate and methacryate, but are not limited thereto. By copolymerizing these monomers, the water- and oil-repellency and stainproofing properties as well as various characteristics (e.g. cleaning resistance, washing resistance and wear resistance of these properties, solubility in solvent, hardness and feeling) can be improved.


20 The weight-average molecular weight of the copolymer (A) is preferably from 2,000 to 1,000,000.

 The amount of the structure unit (I) is preferably from 40 to 90% by weight, more preferably from 50 to 80% by weight; the amount of the structure unit (II) is preferably from 5 to 60% by weight, more preferably from 10 to 40%
25 by weight; the amount of the structure unit (III) is preferably from 5 to 50% by

weight, more preferably from 10 to 40% by weight; and the amount of the structure unit (IV) is preferably from 0.1 to 10% by weight, more preferably from 0.5 to 5% by weight; based on the copolymer (A).

The copolymer (B) is a urethane compound or copolymer having a fluoroalkyl group. The copolymer (B) is a copolymer having (V) a structure unit derived from a monomer having a fluoroalkyl group and a carbon-carbon double bond and (VI) a structure unit derived from a monomer having no fluorine atom, at least one urethane or urea linkage and one carbon-carbon double bond.

The urethane compound (B) having a fluoroalkyl group is preferably a urethane compound represented by the general formula:



wherein Rf^1 is a fluoroalkyl group having 4 to 16 carbon atoms; X^1 is $-\text{R}^1$ -, $-\text{CON}(\text{R}^2)\text{-Q}^1$ -, or $-\text{SO}_2\text{N}(\text{R}^2)\text{-Q}^1$ - (R^1 is an alkylene (for example, $\text{C}_1\text{-C}_{20}$) group; R^2 is a hydrogen atom or a lower (for example, $\text{C}_1\text{-C}_{10}$) alkyl group; Q^1 is an alkylene (for example, $\text{C}_1\text{-C}_{20}$) group); A^1 and A^2 are respectively $-\text{O}$ -, $-\text{S}$ - or $-\text{N}(\text{R}^2)$ - (R^2 is a hydrogen atom or a lower (for example, $\text{C}_1\text{-C}_{10}$) alkyl group); Y^1 is a residue wherein isocyanate is removed from an aromatic or alicyclic diisocyanate; and Z is an alkyl (for example, $\text{C}_1\text{-C}_{20}$) group, an aryl (for example, $\text{C}_6\text{-C}_{20}$) group or $-\text{X}^1\text{-Rf}^1$, or a urethane compound represented by the general formula:



wherein Rf^2 is a fluoroalkyl group having 4 to 16 carbon atoms and X^2 is $-\text{R}^1$ -, $-\text{CON}(\text{R}^2)\text{-Q}^1$ - or $-\text{SO}_2\text{N}(\text{R}^2)\text{-Q}^1$ - (R^1 is an alkylene (for example, $\text{C}_1\text{-C}_{20}$) group; R^2 is a hydrogen atom or a lower (for example, $\text{C}_1\text{-C}_{10}$) alkyl group; Q^1 is an





alkylene (for example, C₁-C₂₀) group); A³ is -O-, -S- or -N(R³)- (R³ is a hydrogen atom or a lower (for example, C₁-C₁₀) alkyl group); Y² is a residue wherein isocyanate is removed from an aromatic or alicyclic diisocyanate; and W is a hydrophilic group.


- 5 Specific examples of the structure unit (V) in the copolymer (B) are the same as those of the above structure unit (I).

The monomer (VI) having no fluorine atom, at least one urethane or urea linkage and one carbon-carbon double bond can be obtained by reacting:



- (a) a compound having at least two isocyanate groups,
 10 (b) a compound having one carbon-carbon double bond and at least one hydroxyl or amino group, and
 (c) a compound having one hydroxyl or amino group.

Examples of the compound (a) are as follows.









5




10




15



20







15

25





Examples of triisocyanate and polyisocyanate are as follows.









CN(C)C(C)(C)C(=O)OCC1=CC=C(C)C(=C1)C(=O)NCC2=CC=C(C)C(=C2)C(=O)NCC3=CC=C(C)C(=C3)C(=O)NO=C(N)c1ccc(cc1)C(c2ccc(cc2)N=C=O)c3ccc(cc3)N=C=OO=C#Nc1ccc(Oc2ccc(S(=O)(=O)c3ccc(N=C=O)cc3)cc2)cc1Cc1ccc(NC(=O)N2C(=O)N(Cc3ccc(NC=O)cc3)C(=O)N2C(=O)N(Cc4ccc(NC=O)cc4)C(=O)N2)cc1












25

The compound (b) may be, for example, a compound represented by the following formulas:





wherein R^1 is a hydrogen atom or a methyl group; p is from 0 to 300 (for example, 1 to 20); and X is as follows:





wherein p, m and n are respectively a number of 1 to 300.

The compound (c) may be a compound represented by the formula:




wherein R^2 and R^3 are the same or different and may contain a hetero atom, and are respectively a C_1 - C_{22} alkyl group or an aromatic or alicyclic group (preferably having 6 to 30 carbon atoms). Preferable groups of R^2 and R^3 are C_8H_{17} , C_7H_{35} , C_4H_9 and cyclohexyl.

10 Examples of the compound (c) are butyl alcohol, 2-ethylhexyl alcohol, lauryl alcohol, stearyl alcohol, oleyl alcohol, benzyl alcohol, cyclohexyl alcohol, 2-ethylhexylamine and sterylamine.

The compounds (a), (b) and (c) may be reacted in a molar ratio of 1:1:1, when the compound (a) is diisocyanate, or 1:1:2 when the compound (a) is
15 triisocyanate.

In the copolymer (B), a weight ratio of the monomer (V) to the monomer (VI) is from 5:95 to 95:5, preferably from 20:80 to 95:5. The weight-average molecular weight of the copolymer (B) may be from 500 to 1,000,000.

The copolymer (C) comprises at least two (meth)acrylic monomers
20 containing no fluorine. The (meth)acrylic monomer containing no fluorine is preferably represented by the general formula:



wherein X^1 is a hydrogen atom or a methyl group; and X^2 is a linear or branched C_nH_{2n+1} group ($n=1-5$).

25 The copolymer (C) may be methyl methacrylate (MMA)/ethyl

methacrylate (EMA) copolymer.

The weight-average molecular weight of the copolymer (C) is preferably from 1,000 to 1,000,000. More preferably, it is from 100,000 to 200,000.

The amount of methyl methacrylate (MMA) is preferably from 40 to 95% by weight, more preferably from 75 to 85%, and the amount of ethyl methacrylate (EMA) is preferably from 5 to 60% by weight, more preferably from 15 to 25%, based on the copolymer (B) which is the MMA/EMA copolymer.

The stainproofing agent preferably contains 0 to 99 parts by weight of the copolymer (A), 0.1 to 99 parts by weight of the component (B) and 0.1 to 99 parts by weight of the copolymer (C).

The copolymers (A) and (C) in the present invention can be normally produced by any polymerization method, and the conditions of the polymerization reaction can also be optionally selected. Examples of the polymerization method include a solution polymerization and an emulsion polymerization. Among them, the emulsion polymerization is particularly preferable.

The method for production of the copolymer (A) will be described in detail.

In the solution polymerization, there can be used a method of dissolving the monomer (I), monomer (II) and crosslinking monomer (IV) in an organic solvent in the presence of a polymerization initiator, charging vinyl chloride (III) after substitution with nitrogen, and heating the mixture with stirring at the temperature within the range from 50 to 120°C for 1 to 10 hours. Examples of the polymerization initiator include azobisisobutyronitrile, benzoyl peroxide, di-t-butyl peroxide, lauryl peroxide, cumene hydroperoxide, t-butyl peroxyphthalate,

and diisopropyl peroxydicarbonate. The polymerization initiator can be used in the amount within the range from 0.01 to 5 parts by weight based on 100 parts by weight of the monomers (I) to (IV).

The organic solvent is inert to the monomers (I) to (IV) and dissolves them. Examples of the organic solvent include pentane, hexane, heptane, octane, cyclohexane, benzene, toluene, xylene, petroleum ether, tetrahydrofuran, 1,4-dioxane, methyl ethyl ketone, methyl isobutyl ketone, ethyl acetate, butyl acetate, 1,1,2,2-tetrachloroethane, 1,1,1-trichloroethane, trichloroethylene, perchloroethylene, tetrachlorodifluoroethane and trichlorotrifluoroethane. The organic solvent can be used in the amount within the range from 50 to 1,000 parts by weight based on 100 parts by weight of total amount of the monomers (I) to (IV).

In the emulsion polymerization, there can be used a method of emulsifying the monomer (I), monomer (II) and crosslinking monomer (IV) in water in the presence of a polymerization initiator and an emulsifying agent, charging vinyl chloride (III) after substitution with nitrogen, and copolymerizing with stirring at the temperature within the range from 50 to 80°C for 1 to 10 hours. As the polymerization initiator, for example, water-soluble initiators (e.g. benzoyl peroxide, lauroyl peroxide, t-butyl perbenzoate, 1-hydroxycyclohexyl hydroperoxide, 3-carboxylpropionyl peroxide, acetyl peroxide, azobisisobutylamidine dihydrochloride, azobisisobutyronitrile, sodium peroxide, potassium persulfate and ammonium persulfate) and oil-soluble initiators (e.g. azobisisobutyronitrile, benzoyl peroxide, di-t-butyl peroxide, lauryl peroxide, cumene hydroperoxide, t-butyl peroxyvalate and diisopropyl peroxydicarbonate) can be used. The polymerization initiator may be used in

the amount within the range from 0.01 to 5 parts by weight based on 100 parts by weight of the monomers.

In order to obtain a copolymer dispersion in water, which is superior in storage stability, it is desirable that the monomers are atomized in water by using an emulsifying device capable of applying a strong shattering energy (e.g. a high-pressure homogenizer and a ultrasonic homogenizer) and then polymerized in the presence of the oil-soluble polymerization initiator. As the emulsifying agent, various emulsifying agents such as an anionic emulsifying agent, a cationic emulsifying agent and a nonionic emulsifying agent can be used in the amount within the range from 0.5 to 10 parts by weight based on 100 parts by weight of the monomers. The anionic and/or nonionic emulsifying agents are preferably used. When the monomers (I) to (IV) are not completely compatibilized, a compatibilizing agent capable of sufficiently compatibilizing them (e.g. a water-soluble organic solvent and a low-molecular weight monomer) is preferably added to these monomers. By the addition of the compatibilizing agent, the emulsifiability and copolymerizability can be improved.

Examples of the water-soluble organic solvent include acetone, methyl ethyl ketone, ethyl acetate, propylene glycol, dipropylene glycol monomethyl ether, dipropylene glycol, tripropylene glycol and ethanol. The water-soluble organic solvent may be used in the amount within the range from 1 to 50 parts by weight, e.g. from 10 to 40 parts by weight, based on 100 parts by weight of water. Examples of the low-molecular weight monomer include methyl methacrylate, glycidyl methacrylate and 2,2,2-trifluoroethyl methacrylate. The low-molecular weight monomer may be used in the amount within the range

from 1 to 50 parts by weight, e.g. from 10 to 40 parts by weight, based on 100 parts by weight of total amount of monomer (I) and monomer (II).

The urethane compound (V) having a fluoroalkyl group can be normally produced by the addition reaction of diisocyanate ($\text{OCN-Y}^1\text{-NCO}$), a fluorine-
 5 containing compound $\text{Rf}^1\text{-X}^1\text{-A}^1\text{-H}$ (e.g. 2-perfluoroalkyl ethanol) and a compound $\text{Z-A}^2\text{-H}$ (e.g. methanol) or W-H (e.g. polyoxyethylene glycol monomethyl ether).

Dispersion of the urethane compound having a fluoroalkyl group into the medium mainly comprising water can be conducted by various methods.
 10 For example, there can be used a method of stirring a mixture of an urethane compound having a fluoroalkyl group and an aqueous medium at high speed under heating and then cooling the reaction solution to room temperature, and a method of adding dropwise a water-soluble organic solvent solution of an urethane compound having a fluoroalkyl group into water under stirring or a
 15 method of adding dropwise water to the contrary.

The copolymer (B) having structure unit (V) and structure unit (VI) can be produced by the solution polymerization, the emulsion polymerization or the suspension polymerization.

The copolymers (A) and (B) in the present invention can be produced by
 20 the solution polymerization in an organic solvent. Examples of the organic solvent include ketones (e.g. acetone, methyl ethyl ketone and methyl isobutyl ketone), esters (e.g. ethyl acetate, propyl acetate and butyl acetate), alcohols (e.g. ethanol, isopropanol, butanol, 1,3-butanediol and 1,5-pentanediol), halogenated hydrocarbons (e.g. perchloroethylene, Trichlene
 25 (trichloroethylene), 1,1-dichloro-2,2,3,3,3-pentafluoropropane, 1,3-dichloro-

1,2,2,3,3,3-pentafluoropropane and 1,1-dichloro-1-fluoroethane (HCFC-141b)); hydrocarbons (such as octane, petroleum, toluene and xylene), dipropylene glycol, dipropylene glycol monomethyl ether, tripropylene glycol monomethyl ether, polypropylene glycol, triethylene glycol dimethyl ether, propylene glycol and ethylene glycol.

Preferable organic solvents are ketones (e.g. methyl ethyl ketone and methyl isobutyl ketone), ethyl acetate and 1,1-dichloro-1-fluoroethane.

The copolymers (A) and (B) can also be produced in an aqueous suspension. The monomer can be emulsion-polymerized by using water, an emulsifying agent and, if necessary, an organic solvent. The mixture may be polymerized after previously emulsifying by a high-pressure emulsifier. As the emulsifying agent, various emulsifying agents (e.g. anionic, cationic or nonionic emulsifying agents) can be used in the amount within the range from 0.5 to 10 parts by weight based on 100 parts by weight of the monomer. It is preferable to use the anionic and/or nonionic emulsifying agents.

Examples of the anionic emulsifying agent include sodium lauryl sulfate, lauryl sulfate triethanolamine, sodium polyoxyethylene lauryl ether sulfate, sodium polyoxyethylene nonylphenyl ether sulfate, polyoxyethylene lauryl ether sulfate triethanolamine, sodium cocoylsarcosine, sodium N-cocoylmethyltaurine, sodium polyoxyethylene (coconut)alkyl ether sulfate, sodium diether hexylsulfosuccinate, sodium α -olefin sulfonate, sodium lauryl phosphate, sodium polyoxyethylene lauryl ether phosphate and perfluoroalkyl carboxylate salt (manufactured by Daikin Industries Ltd., under the trade name of UNIDINE DS-101 and 102).

Examples of the cationic emulsifying agent include dialkyl(C₁₂-

C₂₂)dimethylammonium chloride, alkyl(coconut)dimethylbenzylammonium chloride, octadecylamine acetate salt, tetradecylamine acetate salt, tallow alkylpropylenediamine acetate salt, octadecyltrimethylammonium chloride, alkyl(tallow)trimethylammonium chloride, dodecyltrimethylammonium chloride, alkyl(coconut)trimethylammonium chloride, hexadecyltrimethylammonium chloride, behenyltrimethylammonium chloride, alkyl(tallow)imidazoline quaternary salt, tetradecylmethylbenzylammonium chloride, octadecyldimethylbenzylammonium chloride, dioleyldimethylammonium chloride, polyoxyethylene dodecylmonomethylammonium chloride, polyoxyethylene alkyl(C₁₂-C₂₂)benzylammonium chloride, polyoxyethylene laurylmonomethyl ammonium chloride, 1-hydroxyethyl-2-alkyl(tallow)imidazoline quaternary salt, silicone cationic emulsifying agent having a siloxane group as a hydrophobic group and a fluorine-containing cationic emulsifying agent having a fluoroalkyl group as a hydrophobic group (manufactured by Daikin Industries Ltd., under the trade name of UNIDAIN DS-202).

Examples of the nonionic emulsifying agent include polyoxyethylene lauryl ether, polyoxyethylene tridecyl ether, polyoxyethylene cetyl ether, polyoxyethylene polyoxypropylene cetyl ether, polyoxyethylene stearyl ether, polyoxyethylene oleyl ether, polyoxyethylene nonylphenyl ether, polyoxyethylene octylphenyl ether, polyoxyethylene monolaurate, polyoxyethylene monostearate, polyoxyethylene monooleate, sorbitan monolaurate, sorbitan monostearate, sorbitan monopalmitate, sorbitan monostearate, sorbitan monooleate, sorbitan sesquioleate, sorbitan trioleate, polyoxyethylene sorbitan monolaurate, polyoxyethylene sorbitan

monopalmitate, polyoxyethylene sorbitan monostearate, polyoxyethylene sorbitan monooleate, polyoxyethylene polyoxypropylene block polymer, polyglycerin fatty acid ester, polyether modified silicone oil (manufactured by Toray Dow Corning Co., Ltd., under the trade names of SH3746, SH3748, SH3749 and SH3771), perfluoroalkyl ethylene oxide adduct (manufactured by Daikin Industries Ltd., under the trade names of UNIDINE DS-401 and DS-403), fluoroalkyl ethylene oxide adduct (manufactured by Daikin Industries Ltd., under the trade name of UNIDINE DS-406) and perfluoroalkyl oligomer (manufactured by Daikin Industries Ltd., under the trade name of UNIDINE DS-451).

Examples of the organic solvent used in the emulsion polymerization are the same as those used in the solution polymerization.

In the polymerization, polymerization initiators and/or ionizing radiations (e.g. γ -ray) are used to initiate the polymerization. Examples of the polymerization initiator are an organic peroxide, an azo compound and persulfate.

Examples of the organic peroxide include t-butyl peroxy-pivalate, benzoyl peroxide, lauroyl peroxide, di-t-butyl peroxide and diisopropyl peroxydicarbonate. Examples of the azo compound include 2,2'-azobis-isobutyronitrile and 2,2'-azobis(2-methylbutyronitrile).

The copolymer (C) can be produced by the procedure which has hitherto been used (or almost the same procedure as that in case of the copolymer (A)).

The stainproofing agent can be obtained by mixing a liquid containing the copolymer (A), a urethane compound or urethane-containing copolymer (B) and a liquid containing the copolymer (C), which are separately prepared, and

optionally adding a medium (e.g. water and an organic solvent).

5 The stainproofing agent of the present invention can be applied to the surface of the material to be treated by the method which has hitherto been known. There can be normally used a method of diluting the stainproofing agent with the organic solvent or water, applying the solution to the surface of the material to be treated (e.g. a carpet fabric, a carpet yarn or raw cotton) by a known method (e.g. dip coating, spray coating and foam coating). If necessary, the stainproofing agent may be applied together with a suitable crosslinking agent, followed by curing. It is also possible to add other water repellents and oil repellents, and mothproofing agents, textile softeners, antimicrobial agents, flame retardants, antistatic agents, paint fixing agents and crease-proofing agents to the stainproofing agent of the present invention and to use them in combination. In case of the dip coating, the solid content of the treatment liquid (namely, the concentration of the components (A) to (C) in the dipping liquid) may be from 0.05 to 10% by weight. In case of the spray coating, the solid content of the treatment liquid (namely, the concentration of the components (A) to (C) in the treatment liquid) may be from 0.1 to 5% by weight. A stain blocker may be used in combination. When using the stain blocker, the anionic or nonionic emulsifying agent is preferably used.

20 The product to be treated with the stainproofing agent of the present invention is preferably a textile, particularly a carpet. Examples of the textile include animal- or vegetable-origin natural fibers such as cotton, hemp, wool and silk; synthetic fibers such as polyamide, polyester, polyvinyl alcohol, polyacrylonitrile, polyvinyl chloride and polypropylene; semisynthetic fibers such as rayon and acetate; inorganic fibers such as glass fiber, carbon fiber

25

and asbestos fiber; and a mixture of these fibers. The stainproofing agent of the present invention can be suitably used in carpets of nylon or polypropylene because of excellent resistance to a detergent solution and brushing (mechanical).

5 The textile may be in any form of a fiber as such, a yarn and a cloth. When the carpet is treated with the stainproofing agent of the present invention, the carpet may be formed after treating fibers or yarns with the stainproofing agent, or the formed carpet may be treated with the stainproofing agent of the present invention. Examples of the material to be treated with the stainproofing agent of the present invention include glass, paper, wood, hide, asbestos,
10 brick, cement, metal and oxide, ceramics, plastics, coated surface and plaster in addition to textile.

PREFERRED EMBODIMENTS OF THE INVENTION

15 The present invention will be illustrated by the following Examples which do not limit the present invention. In the Examples, the amount is by weight unless specified otherwise.

20 The stainproofing agents obtained in the Examples and Comparative Examples were evaluated as follows. Each emulsion obtained in the Examples and Comparative Examples is diluted with water to prepare a liquid with a solid content of 3%, which is used as a treatment liquid. This treatment liquid is sprayed on a nylon loop-pile carpet fabric (non-backed product) so that a treating amount is 100 g/m², and the treated carpet fabric is dried with heating at 130°C for 7 minutes. The water repellency, oil repellency and stainproofing properties before and after cleaning test are evaluated. The cleaning test
25 method and the evaluation method of the water repellency, oil repellency and

stainproofing properties shown in the Examples and Comparative Examples are as follows.

The cleaning test was conducted according to the method of JIS (Japanese Industrial Standard)-L-1021-1979.

5 The water repellency is expressed by the water repellency No. (cf. the following Table 1) determined by the spray method according to JIS-L-1092.

The oil repellency is determined by dropping several drops (diameter: about 4 mm) of a test solution shown in AATCC-TM-118-1966 (Table 2) on two positions of the surface of a test cloth and observing the penetration state of the drops after 30 seconds. A maximum point of the oil repellency given by the test solution causing no penetration is taken as the oil repellency.

A carpet is stained with a dry soil having the composition shown in Table 3 according to JIS-L-1021-1979. After the excess dry soil on the surface is sucked with an electrical cleaner, the brightness of the surface is measured by a colorimeter and a staining degree is calculated from the following equation, which is taken for evaluation of dry soiling stainproof properties.

$$\text{Stainproof degree (\%)} = [(L_0 - L)/L_0] \times 100$$

(wherein L_0 : brightness before staining, L : brightness after staining)

The oil repellency in case of treating a carpet was evaluated in the same manner as in treating a normal fiber.

Table 1

Water repellency No.	State
100	No wet on the surface
90	Slight wet on the surface
80	Partial wet on the surface
70	Wet on the surface
50	Wet over the whole surface
0	Complete wet on the front and back surfaces

Table 2

Oil repellency	Test solution	Surface tension (dyn/cm, 25°C)
8	n-Heptane	20.0
7	n-Octane	21.8
6	n-Decane	23.5
5	n-Dodecane	25.0
4	n-Tetradecane	26.7
3	n-Hexadecane	27.3
2	n-Hexadecane/Nujol (35/65 by weight)	29.6
1	Nujol	31.2
0	Inferior to 1	-

Table 3

Component	Weight ratio (%)
Peat moss	38
Portland cement (JIS R 5210)	17
White clay (JIS K 8746)	17
Diatomaceous earth (JIS K 8330)	17
Carbon black (JIS K 5107)	1.75
Iron oxide (III) for ferrite (JIS K 1462)	0.5
Nujol	8.75

Preparative Example 1 (vinyl chloride-containing FA/StA copolymer anionic emulsion + fluoroalkyl group-containing urethane + blender emulsion)

10 $\text{CH}_2=\text{CHCOO}(\text{CH}_2)_2(\text{CF}_2\text{CF}_2)_n\text{CF}_2\text{CF}_3$ (a mixture wherein a weight ratio of compounds wherein n is 3, 4 and 5 is 5:3:1) (SFA), stearyl acrylate (StA), 2-hydroxyethyl methacrylate (2EHA), diacetoneacrylamide (DAAM), 3-chloro-2-hydroxypropyl methacrylate (Topolene M), deionized water, n-laurylmercaptan (LSH) as a chain transfer agent, ammonium polyoxyethylene alkyl phenyl ether sulfate (Hitenol N-17), polyoxyethylene alkylphenyl ether (Nonion HS-220),
 15 polyoxyethylene sorbitan monolaurate (Nonion LT-221) and dipropylene glycol monomethyl ether (DPM) were mixed in the amount shown in Table 4 to prepare a mixed liquid.


20 This mixed liquid was heated to 60°C and emulsified by a high-pressure homogenizer. The resulting emulsion was charged in a 1 L autoclave and dissolved oxygen was removed by substitution with nitrogen. Then, vinyl chloride (VCl) having a purity of 99% was charged in the amount shown in Table 4 and ammonium persulfate (APS) as an initiator was charged in the

amount shown in Table 4. Under stirring, the copolymerization reaction was conducted at 60°C for 8 hours.

A gas chromatography analysis revealed that at least 99% of monomers were polymerized.

348 g of 2,4-tolylene diisocyanate was dissolved in 348 g of methyl isobutyl ketone (MIBK) and the solution was purged with nitrogen, stirred and then heated to 80°C. When the temperature reached 80°C, two drops of dibutyltin laurate were added and, at the same time, dropwise addition of 2-perfluoroalkyl ethanol (260 g) was initiated and added dropwise, slowly, over 2 hours. After the completion of the dropwise addition, 260 g of ethanol was added dropwise slowly over 2 hours. After the completion of the dropwise addition, the stirring was continued at 80°C for 2 hours. Then, MIBK was distilled off under reduced pressure to obtain 868 g of an yellow transparent viscous liquid. IR revealed that -NCO group completely disappeared, and ¹H-NMR and ¹³C-NMR revealed the disappearance of -OH, the formation of an urethane linkage and the existence of a double bond.

A chemical structure of this product was as follows:



(a mixture wherein a molar ratio of compounds wherein n is 3, 4 and 5 is about 5:3:1)

100 g of this compound, 50 g of deionized water and 10 g of ethylene glycol monomethyl ether were charged, and then the temperature was raised to

about 100°C. The mixture was stirred under high shear for 30 minutes and then cooled to room temperature.

The copolymer emulsion and fluoroalkyl group-containing urethane emulsion obtained by the above production process and a blender emulsion [a
5 copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA) (weight ratio of MMA to EMA = 80:20)] were blended so that a weight ratio of each solid content of the emulsions was 1:1:1.

Preparative Example 2 (vinyl chloride-containing FA/StA copolymer anionic
10 emulsion + urethane linkage-containing monomer/FA copolymer + blender emulsion)

$\text{CH}_2=\text{CHCOO}(\text{CH}_2)_2(\text{CF}_2\text{CF}_2)_n\text{CF}_2\text{CF}_3$ (a mixture wherein a weight ratio
of compounds where in n is 3, 4 and 5 is 5:3:1) (SFA), stearyl acrylate (StA), 2-
hydroxyethyl methacrylate (2EHA), diacetoneacrylamide (DAAM), 3-chloro-2-
hydroxypropyl methacrylate (Topolene M), deionized water, n-laurylmercaptan
15 (LSH), polyoxyethylene alkyl phenyl ether (Nonion HS-220), polyoxyethylene sorbitan monolaurate (Nonion LT-221) and dipropylene glycol monomethyl ether (DPM) were mixed in the amount shown in Table 4.


This mixed liquid was heated to 60°C and emulsified by a high-pressure homogenizer. The resulting emulsion was charged in a 1 L autoclave and the
20 dissolved oxygen was removed by substitution with nitrogen. Then, vinyl chloride (VCl) having a purity of 99% was charged in the amount shown in Table 4 and ammonium persulfate (APS) as an initiator was charged in the amount shown in Table 4. Under stirring, the copolymerization reaction was conducted at 60°C for 8 hours.

25 A gas chromatography analysis revealed that at least 99% of monomers

were polymerized.

348 g of 2,4-tolylene diisocyanate was dissolved in 348 g of methyl isobutyl ketone (MIBK) and the solution was purged with nitrogen, stirred and then heated to 80°C. When the temperature reached 80°C, two drops of
 5 dibutyltin laurate were added and, at the same time, dropwise addition of 2-ethylhexyl alcohol (260 g) was initiated and added dropwise, slowly, over 2 hours. After the completion of the dropwise addition, 260 g of 2-hydroxyethyl methacrylate was added dropwise, slowly, over 2 hours. After the completion of the dropwise addition, the stirring was continued at 80°C for 2 hours. Then,
 10 MIBK was distilled off under reduced pressure to obtain 868 g of an yellow transparent viscous liquid. IR revealed that -NCO group completely disappeared, and ¹H-NMR and ¹³C-NMR revealed the disappearance of -OH, the formation of an urethane linkage and the existence of a double bond.

A chemical structure of this product was as follows:



In a flask equipped with a stirrer, a thermometer and a reflux condenser, 120 g of the resulting product and 80 g of CH₂=CHCOO(CH₂)₂(CF₂CF₂)_n CF₂CF₃ (a mixture wherein a weight ratio of compounds wherein n is 3, 4 and 5
 25 is 5:3:1) (SFA) were charged and dissolved in 800 g of MIBK. Then, the

solution was stirred, purged with nitrogen and heated to 60°C. At one hour after the beginning of the purging with nitrogen, it was confirmed that the inner temperature was 60°C. 4 g of t-butyl peroxyvalate (manufactured by Nippon Yushi Co., Ltd. under the trade name of Perbutyl PV) was added to initiate the polymerization.

At eight hours after the beginning of the polymerization, a gas chromatography analysis revealed that at least 99% of monomers were reacted. A pale yellow liquid having a solid content of 20% was obtained.

Two copolymer emulsions obtained in the above production process and a blender emulsion (a copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA)(weight ratio of MMA to EMA = 80:20)) were blended so that a weight ratio of each solid content of the emulsions was 1:1:1.

Comparative Preparative Example 1 (vinyl chloride-containing FA/StA copolymer anionic emulsion + blender emulsion)

The vinyl chloride-containing FA/StA copolymer emulsion obtained in Preparative Example 1 and a blender emulsion (a copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA)(weight ratio of MMA to EMA = 80:20)) were blended so that a weight ratio of each solid content was 1:1.

Comparative Preparative Example 2 (fluoroalkyl group-containing urethane + blender emulsion)

The fluoroalkyl group-containing urethane obtained in Preparative Example 1 and a blender emulsion (a copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA)(weight ratio of MMA to EMA = 80:20)), were blended so that a weight ratio of each solid content was 1:1.

Comparative Preparative Example 3 (urethane linkage-containing monomer/FA copolymer + blender emulsion)

The urethane linkage-containing monomer/FA copolymer emulsion obtained in Preparative Example 2 and a blender emulsion (a copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA)(weight ratio of MMA to EMA = 80:20)) were blended so that a weight ratio of each solid content was 1:1.

Example 1 (vinyl chloride-containing FA/StA copolymer anionic emulsion + fluoroalkyl group-containing urethane + blender emulsion)

The emulsion mixture prepared in Preparative Example 1 was diluted with water to prepare a liquid with a solid content of 3%, which was used as a treating liquid. This treating liquid was sprayed on a nylon pile carpet fabric (non-backed product) so that a treating amount was 100 g/m², and the treated carpet fabric was dried with heating at 130°C for 7 minutes. The water repellency, oil repellency and stainproofing properties were evaluated before and after cleaning. The results are shown in Table 5.

Example 2 (vinyl chloride-containing FA/StA copolymer anionic emulsion + urethane linkage-containing monomer/FA copolymer + blender emulsion)

The water repellency, oil repellency and stainproofing properties before and after cleaning of the emulsion mixture prepared in Preparative Example 2 were evaluated in the same manner as in Example 1. The results are shown in Table 5.

Comparative Example 1 (vinyl chloride-containing FA/StA copolymer anionic emulsion + blender emulsion)

The water repellency, oil repellency and stainproofing properties before

and after cleaning of the emulsion prepared in Comparative Preparative Example 1 were evaluated in the same manner as in Example 1. The results are shown in Table 5.

Comparative Example 2 (fluoroalkyl group-containing urethane emulsion +
5 blender emulsion)

The water repellency, oil repellency and stainproofing properties before and after cleaning of the emulsion prepared in Comparative Preparative Example 2 were evaluated in the same manner as in Example 1. The results are shown in Table 5.

Comparative Example 3 (urethane linkage-containing monomer/FA copolymer
10 + blender emulsion)

The water repellency, oil repellency and stainproofing properties before and after cleaning of the emulsion prepared in Comparative Preparative Example 3 were evaluated in the same manner as in Example 1. The results
15 are shown in Table 5.

Comparative Example 4 (blender emulsion)

The blender emulsion (copolymer emulsion of methyl methacrylate (MMA)/ethyl methacrylate (EMA) (weight ratio of MMA to EMA = 80:20)) was diluted with water to prepare a liquid with a solid content of 3%, which was
20 used as a treating liquid. The water repellency, oil repellency and stainproofing properties before and after cleaning of this treating liquid emulsion were evaluated in the same manner as in Example 1. The results are shown in Table 5.

Table 4

		Preparative Example 1	Preparative Example 2	Comparative Preparative Example 1
Monomer composition (wt%)	SFA	134	134	134
	StA	37	37	37
	VCl	28	28	28
	2EHA	3.5	3.5	3.5
	DAAM	1.8	1.8	1.8
	Topolene M	1.8	1.8	1.8
Emulsifying agent (based on monomer (% by weight))	Hitenol N-17	3.3	3.3	3.3
	HS-220	7.9	7.9	7.9
	LT-221	5.3	5.3	5.3
Other (based on monomer (% by weight))	LSH	3.5	3.5	3.5
	DPM	44	44	44
	APS	1.2	1.2	1.2
	Deionized water	330	330	330

Table 5

		Example 1	Example 2	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4
Before cleaning	Oil repellency	5	5	4	4	4	0
	Water repellency	60	60	60	60	60	0
	Dry soil stainproof properties	18	18	18	18	18	18
After cleaning	Oil repellency	5	5	4	2	2	0
	Water repellency	60	60	60	20	20	0
	Dry soil stainproof properties	18	18	18	36	36	25

WHAT IS CLAIMED IS:

1. A stainproofing agent comprising:

(A) a fluoroalkyl group-containing copolymer comprising

(I) a structure unit derived from a monomer having a fluoroalkyl group,

(II) a structure unit derived from a monomer containing no fluorine,

(III) a structure unit derived from vinyl chloride, and

(IV) a structure unit derived from a crosslinking monomer;

(B) a urethane compound having a fluoroalkyl group, or a copolymer having

(V) a structure unit derived from a monomer having a fluoroalkyl group and a carbon-carbon double bond, and

(VI) a structure unit derived from a monomer which contains no fluorine atom and has at least one urethane or urea linkage and one carbon-carbon double bond; and

(C) an acrylic copolymer containing no fluorine.

2. The stainproofing agent according to claim 1, wherein the monomer constituting the structure unit (I) is represented by the general formula:




wherein Rf is a linear or branched fluoroalkyl group having 3 to 20 carbon atoms;

R¹ is a linear or branched alkylene group having 1 to 20 carbon atoms, a group of -SO₂N(R³)R⁴- or a group of -CH₂CH(OR⁵)CH₂- (R³ is an alkyl group having 1 to 10 carbon atoms; R⁴ is a linear or branched alkylene group having 1 to 10 carbon atoms; and R⁵ is a hydrogen atom or an acyl group having 1 to 10 carbon atoms); and


R² is a hydrogen atom or a methyl group.

3. The stainproofing agent according to claim 1, wherein the monomer constituting the structure unit (II) is acrylate represented by the general formula:



5 wherein B¹ is a hydrogen atom or a methyl group; and B² is an alkyl group represented by C_nH_{2n+1} (n=1-30).

4. The stainproofing agent according to claim 1, wherein the urethane compound (B) having a fluoroalkyl group is an urethane compound, represented by the general formula:



wherein Rf¹ is a fluoroalkyl group having 4 to 16 carbon atoms; X¹ is -R¹-, -CON(R²)-Q¹- or -SO₂N(R²)-Q¹- (R¹ is an alkylene group; R² is a hydrogen atom or a lower alkyl group and; Q¹ is an alkylene group); A¹ and A² are respectively -O-, -S- or -N(R²)- (R² is a hydrogen atom or a lower alkyl group); Y¹ is a residue wherein isocyanate is removed from an aromatic or alicyclic diisocyanate; and Z is an alkyl group, an aryl group or -X¹-Rf¹, or an urethane compound represented by the general formula:



wherein Rf² is a fluoroalkyl group having 4 to 16 carbon atoms and is X² is -R¹-, -CON(R²)-Q¹- or -SO₂N(R²)-Q¹- (R¹ is an alkylene group; R² is a hydrogen atom or a lower alkyl group and ; Q¹ is an alkylene group); A³ is -O-, -S- or -N(R³)- (R³ is a hydrogen atom or a lower alkyl group); Y² is a residue wherein isocyanate is removed from an aromatic or alicyclic diisocyanate; and W is a hydrophilic group.

25 5. The stainproofing agent according to claim 1, wherein the monomer


constituting the structure unit (VI) is a monomer obtained by reacting:

(a) a compound having at least two isocyanate groups,

(b) a compound having one carbon-carbon double bond and at least one hydroxyl or amino group, and

5 (c) a compound having one hydroxyl or amino group.

6. The stainproofing agent according to claim 1, wherein the copolymer (C) is derived from at least two (meth)acrylic monomers containing no fluorine, and the (meth)acrylic monomer containing no fluorine is represented by the general formula:



wherein X^1 is a hydrogen atom or a methyl group; and X^2 is a linear or branched $\text{C}_n\text{H}_{2n+1}$ ($n=1-5$).

7. The stainproofing agent according to claim 1, wherein the amount of the structure unit (I) is from 40 to 90% by weight, the amount of the structure unit (II) is from 5 to 60% by weight, the amount of the structure unit (III) is from 5 to 50% by weight, and the amount of the structure unit (IV) is from 0.1 to 10% by weight, respectively, based on the copolymer (A).

8. The stainproofing agent according to claim 1, wherein the copolymer (A), the urethane compound or urethane-containing copolymer (B) and the copolymer (C) are in the form of an aqueous dispersion in a medium comprising water.

9. The stainproofing agent according to claim 1, wherein the copolymer (A), the urethane compound or urethane-containing the copolymer (B) and the copolymer (C) are in the form of an aqueous dispersion in a medium comprising water, using a nonionic and/or anionic emulsifying agents.

10. A stainproofing agent comprising:

(B) a copolymer having:

(V) a structure unit derived from a monomer having a fluoroalkyl group and carbon-carbon double bond, and

5 (VI) a structure unit derived from a monomer which contains no fluorine atom and has at least one urethane or urea linkage and one carbon-carbon double bond; and

(C) an acrylic copolymer containing no fluorine.

10 11. The stainproofing agent according to claim 1, wherein urethane-containing copolymer (B) and the copolymer (C) are in the form of an aqueous dispersion prepared by dispersing in a medium mainly composed of water.

12. A textile which is treated with the stainproofing agent according to anyone of claims 1 to 11.

13. The textile according to claim 12, which is a carpet.

ABSTRACT OF THE DISCLOSURE

The present invention provides a stainproofing agent having the durability capable of maintaining sufficient water- and oil-repellency as well as stainproofing properties before and after cleaning. Disclosed is a stainproofing agent containing (A) a fluoroalkyl group-containing copolymer having (I) a structure unit derived from a monomer having a fluoroalkyl group, (II) a structure unit derived from a monomer containing no fluorine, (III) a structure unit derived from vinyl chloride, and (IV) a structure unit derived from a crosslinking monomer; (B) a urethane compound having a fluoroalkyl group, or a copolymer having (V) a structure unit derived from a monomer having a fluoroalkyl group and a carbon-carbon double bond, and (VI) a structure unit derived from a monomer which contains no fluorine atom and has at least one urethane or urea linkage and one carbon-carbon double bond; and (C) an acrylic copolymer containing no fluorine.

BIRCH, STEWART, KOLASCH & BIRCH, LLP

COMBINED DECLARATION AND POWER OF ATTORNEY

ATTORNEY DOCKET NO.

20-4362P

FOR PATENT AND DESIGN APPLICATIONS

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Insert Title:

STAINPROOFING AGENT

Fill in Appropriate
Information -
For Use Without
Specification
Attached:

the specification of which is attached hereto. If not attached hereto,

the specification was filed on _____ as
United States Application Number _____; and /or

the specification was filed on _____ as PCT
International Application Number _____; and was
amended under PCT Article 19 on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 (a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Insert Priority
Information:
(if appropriate)

Prior Foreign Application(s)

5358/1997	Japan	Jan. 16, 1997
(Number)	(Country)	(Month/Day/Year Filed)
_____	_____	_____
(Number)	(Country)	(Month/Day/Year Filed)
_____	_____	_____
(Number)	(Country)	(Month/Day/Year Filed)
_____	_____	_____
(Number)	(Country)	(Month/Day/Year Filed)
_____	_____	_____
(Number)	(Country)	(Month/Day/Year Filed)
_____	_____	_____

Priority Claimed

<input checked="" type="checkbox"/> Yes	<input type="checkbox"/> No
<input type="checkbox"/> Yes	<input type="checkbox"/> No
<input type="checkbox"/> Yes	<input type="checkbox"/> No
<input type="checkbox"/> Yes	<input type="checkbox"/> No
<input type="checkbox"/> Yes	<input type="checkbox"/> No
<input type="checkbox"/> Yes	<input type="checkbox"/> No

I hereby claim the benefit under Title 35, United States Code, §119(e) of any United States provisional application(s) listed below.

Insert Provisional
Application(s):
(if any)

_____	_____
(Application Number)	(Filing Date)
_____	_____
(Application Number)	(Filing Date)

All Foreign Applications, if any, for any Patent or Inventor's Certificate Filed More Than 12 Months (6 Months for Designs) Prior To The Filing Date of This Application:

Insert Requested
Information:
(if appropriate)

_____	_____	_____
Country	Application No.	Date of Filing (Month/Day/Year)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application:

Insert Prior U.S.
Application(s):
(if any)

_____	_____	_____
(Application Number)	(Filing Date)	(Status - patented, pending, abandoned)
_____	_____	_____
(Application Number)	(Filing Date)	(Status - patented, pending, abandoned)

I hereby appoint the following attorneys to prosecute this application and/or an international application based on this application and to transact all business in the Patent and Trademark Office connected therewith and in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the attorneys identified below, unless the inventor(s) or assignee provides said attorneys with a written notice to the contrary:

Terrell C. Birch (Reg. No. 19,382)
Joseph A. Kolasch (Reg. No. 22,463)
Bernard L. Sweeney (Reg. No. 24,448)
Charles Gorenstein (Reg. No. 29,271)
Leonard R. Svensson (Reg. No. 30,330)
Andrew D. Meikle (Reg. No. 32,868)
Joe McKinney Muncy (Reg. No. 32,334)
C. Joseph Faraci (Reg. No. 32,350)

Raymond C. Stewart (Reg. No. 21,066)
James M. Slattery (Reg. No. 28,380)
Michael K. Mutter (Reg. No. 29,680)
Gerald M. Murphy, Jr. (Reg. No. 28,977)
Terry L. Clark (Reg. No. 32,644)
Marc S. Weiner (Reg. No. 32,181)
Andrew F. Reish (Reg. No. 33,443)
Donald J. Daley (Reg. No. 34,313)

Send Correspondence to:

BIRCH, STEWART, KOLASCH & BIRCH, LLP

P.O. Box 747 • Falls Church, Virginia 22040-0747

Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

PLEASE NOTE:
YOU MUST
COMPLETE THE
FOLLOWING:

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of First or Sole
Inventor:
Insert Name of Inventor
Insert Date This
Document is Signed

Insert Residence
Insert Citizenship

Insert Post Office
Address

Full Name of Second
Inventor, if any:

see above

Full Name of Third
Inventor, if any

see above

Full Name of Fourth
Inventor, if any


see above

Full Name of Fifth
Inventor, if any

see above

GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Masayuki	YAMANA	Masayuki Yamana	Jan. 12, 1998
Residence (City, State & Country)		CITIZENSHIP	
Settsu, Osaka, Japan		Japan	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
c/o Yodogawa Works of Daikin Industries Ltd., 1-1, Nishihitotsuya, Settsu, Osaka, Japan			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Ikuo	YAMAMOTO	Ikuo Yamamoto	Jan. 12, 1998
Residence (City, State & Country)		CITIZENSHIP	
Settsu, Osaka, Japan		Japan	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
c/o Yodogawa Works of Daikin Industries Ltd., 1-1, Nishihitotsuya, Settsu, Osaka, Japan			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Teruyuki	FUKUDA	TERUYUKI FUKUDA	Jan. 12, 1998
Residence (City, State & Country)		CITIZENSHIP	
Settsu, Osaka, Japan		Japan	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
c/o Yodogawa Works of Daikin Industries Ltd., 1-1, Nishihitotsuya, Settsu, Osaka, Japan			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
Settsu, Osaka, Japan		Japan	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
c/o Yodogawa Works of Daikin Industries Ltd., 1-1, Nishihitotsuya, Settsu, Osaka, Japan			
GIVEN NAME	FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)		CITIZENSHIP	
Settsu, Osaka, Japan		Japan	
POST OFFICE ADDRESS (Complete Street Address including City, State & Country)			
c/o Yodogawa Works of Daikin Industries Ltd., 1-1, Nishihitotsuya, Settsu, Osaka, Japan			

United States Patent & Trademark Office
Office of Initial Patent Examination – Scanning Division



Application deficiencies found during scanning:

1. Application papers are not suitable for scanning and are not in compliance with 37 CFR 1.52 because:
 - ☐ All sheets must be the same size and either A4 (21 cm x 29.7 cm) or 8-1/2" x 11". Pages _____ do not meet these requirements.
 - ☐ Papers are not flexible, strong, smooth, non-shiny, durable, and white.
 - ☐ Papers are not typewritten or mechanically printed in permanent ink on one side.
 - ☐ Papers contain improper margins. Each sheet must have a left margin of at least 2.5 cm (1") and top, bottom and right margins of at least 2.0 cm (3/4").
 - ☐ Papers contain hand lettering.
2. Drawings are not in compliance and were not scanned because:
 - ☐ The drawings or copy of drawings are not suitable for electronic reproduction.
 - ☐ All drawings sheets are not the same size. Pages must be either A4 (21 cm x 29.7 cm) or 8-1/2" x 11".
 - ☐ Each sheet must include a top and left margin of at least 2.5 cm (1"), a right margin of at least 1.5 cm (9/16") and a bottom margin of at least 1.0 cm (3/8").
3. Page(s) _____ are not of sufficient clarity, contrast and quality for electronic reproduction.
4. Page(s) _____ are missing.
5. OTHER: NO Drawings